


MOLDED GRATINGS

Grating type SCH 40/38C_IFR

Mesh	mm 40 x 40
Thickness	mm 45
Cover thickness	mm 5
Bearing bar	mm 8 upper part
thickness	mm 7 bottom part
Color	Grey RAL 7004



	Polyester Resin
Raw materials	Roving glass fiber + Mat and lath type"E"
	Inorganic fillers without halogens

Stand	dard panels
mm	1000 x 2000
mm	1200 x 3000
Weigh	nt kg/m² 30
tolerance	± mm 5 panel dimensions
wiciance	± mm 2 height

Surface	S	Smooth	Antiskid level R10 V4 norm DIN E51130
Surface	Α	Moulded rough	Antiskid level R13 V4 norm DIN E51130

Reaction to fire	Fire retardant	Spread ≤ 25 norm ASTM E84-98	
Neaction to me	File retardant	Level V-0 norm UL94 Vertical Burning Test	

Ageing resistance	Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m²)
	After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects



M.M. S.r.l.

Via A. Zanussi 300 / 302, 33100 Udine (Italy)
Ph. +39 0432.602218 / 522970 - Fax. +39 0432.522253
info@mmgrigliati.it - www.mmgrigliati.it

SCH 40/38C_IFR

20.05.2009 Rev. 2 COMPANY
WITH QUALITY MANAGEMENT
SYSTEM CERTIFIED BY DNV
=ISO 9001:2000=

LOADS

MAXIMUM SUGGESTED LOADS

Type of support	On the line of the two ends of the panel

Limits determined by	Deflection (load sagging)		
the maximum deflection admitted is 1/100 of the distance between the supports			

DISTRIBUTED LOAD		CONCENTRATED LOAD	
Distance between supports	Load with deflection equal to 1/100	Distance between supports	Load with deflection equal to 1/100
[cm]	[kg/m²]	[cm]	[kg/m]
50	13450	50	4200
70	4900	70	2150
90	2300	90	1300
110	1250	110	850

Limits determined by	Admitted stresses (stress determined by the load)
the maximum adn	nitted stress is 1/5 of the breakdown stress
(safety coefficient is equal t	o 5 – the breakdown stress is 5 times the specified load)

DISTRIBUTED		CONCENTRATED	
LOAD		LOAD	
Distance between supports	Maximum admitted load	Distance between supports	Maximum load admitted
[cm]	[kg/m²]	[cm]	[kg/m]
50	16100	50	4000
70	8200	70	2850
90	4950	90	2200
110	3300	110	1800

The information specified in the above table is to be considered as an average value and variations may reach a ±15%.

The above characteristics are meant as reference values for standard material. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.



M.M. S.r.I.

Via A. Zanussi 300 / 302, 33100 Udine (Italy)
Ph. +39 0432.602218 / 522970 - Fax. +39 0432.522253
info@mmgrigliati.it - www.mmgrigliati.it

SCH 40/38C_IFR

20.05.2009 Rev. 2 COMPANY
WITH QUALITY MANAGEMENT
SYSTEM CERTIFIED BY DNV
=ISO 9001: 2000=