

# MOLDED GRATINGS

Grating typ	e SCH 52	/30_IFR
-------------	----------	---------

Color	Grey RAL 7004		
thickness	mm	5	bottom part
Bearing bar	mm	7	upper part
Height	mm	30	
Clear span	mm	19 >	x 19
Wesn	mm	26 >	x 26 secondary
Maah	mm	52 >	<b>x 52</b> main



	Polyester Resin
Raw materials	Roving glass fiber type"E"
	Inorganic fillers without halogens



	S	Smooth	Antiskid level R10 V10 norm DIN E51130	
Surface	М	Meniscus	Antiskid level R13 V10 norm DIN E51130	
	А	Quartz	Antiskid level R13 V10 norm DIN E51130	

Reaction to fire	Fire retardant	Spread ≤ 25 norm ASTM E84-98		
		Level V-0 norm UL94 Vertical Burning Test		
Ageing resistance	Ageing test made with UV lamp according to ASTM G154-06 and passed with 5 points on the gray range and without evident defects (test made with 1500 hours of exposure to 4 hours alternate cycles at a UV temperature of 60°C and 4 hours at a condensed temperature of 50°C irradiated by UVB 313 nm lamp, radiance 0,71 W/m <sup>2</sup> )			
	After the exposure to heat, cold and humidity cycles according to UNI EN ISO 9142/04 norm (n° 21 cycles type D3) there is no evidence of defects			

#### M.M. S.r.I.

MN

Via A. Zanussi 300 / 302, 33100 Udine (Italy)
Ph. +39 0432.602218 / 522970 - Fax. +39 0432.522253
info@mmgrigliati.it - www.mmgrigliati.it

SCH 52/30_IFR	COMPANY WITH OUALITY MANACEMENT	
20.05.2009	SYSTEM CERTIFIED BY DNV	
Rev. 2	=ISO 9001:2000=	

## LOADS

## MAXIMUM SUGGESTED LOADS

Type of support

On the line of the two ends of the panel

Limits determined by

**Deflection** (load sagging)

the maximum deflection admitted is 1/100 of the distance between the supports

DISTR LOAD	RIBUTED	and the second s	CONCENTRATED LOAD	
Dista	ance between supports	Load with deflection equal to 1/100	Distance between supports	Load with deflection equal to 1/100
	[cm]	[kg/m <sup>2</sup> ]	[cm]	[kg/m]
	50	2000	50	600
	70	700	70	300
	90	300	90	150
	110	110	110	100
1				

All lighter loads are admitted

Limits determined by

### Admitted stresses (stress determined by the load)

the **maximum admitted stress** is 1/5 of the breakdown stress (safety coefficient is equal to 5 – the breakdown stress is 5 times the specified load)

NTRATED	
ce between Maximum	load admitted
[cm] [	kg/m]
50 1	050
70	750
90	550
110 4	450
-	110 4

All lighter loads are admitted

The information specified in the above table is to be considered as an average value and variations may reach a  $\pm 15\%$ .

The above characteristics are meant as reference values for standard material. Even if they are not to be considered as guaranteed characteristics they are based on our experience and are supplied in good faith.



#### M.M. S.r.I.

Via A. Zanussi 300 / 302, 33100 Udine (Italy) Ph. +39 0432.602218 / 522970 - Fax. +39 0432.522253 info@mmgrigliati.it - www.mmgrigliati.it

## SCH 52/30\_IFR

20.05.2009 Rev. 2 COMPANY WITH QUALITY MANAGEMENT SYSTEM CERTIFIED BY DNV =ISO 9001 : 2000=